

PRODUCT NAME

STEPANPOL[®] PS-1752

PRODUCT DESCRIPTION

STEPANPOL PS-1752 is an aromatic polyester polyol.

PERFORMANCE HIGHLIGHTS

This aromatic polyester polyol can be added to polyether flexible slabstock foams to improve the bond strength of the foams when flame laminated to textiles. This polyol offers the greatest increase to bond strength and mechanical properties while maintaining processing latitude.

TYPICAL PROPERTIES

Hydroxyl Number, mg KOH/g _____ 175
Water, % by wt., max. _____ 0.05
Acid Number, mg KOH/g, max. _____ 0.8
Color, Gardner, max. _____ 6

Equivalent Weight _____ 319
OH Functionality _____ 2
Viscosity at 77°F (25°C), cP _____ 3,800
Density at 77°F (25°C), lb/US gal. _____ 10.5

STORAGE

STEPANPOL PS-1752 has a retest period of 24 months in unopened containers. Storage in sealed containers at temperatures of 60-95°F (15-35°C) is recommended.

CLEARANCE STATUS


STEPANPOL PS-1752 is on the Toxic Substances Control Act (TSCA) Inventory.

CAS NUMBER

32472-85-8 and 108-32-7

Stepan[®] and STEPANPOL[®] are registered trademarks of Stepan Company.

VISCOSITY: VARIATION WITH TEMPERATURE



A Material Safety Sheet is available upon request.

All polyurethane foam burns in varying degrees, which in turn liberates toxic gases; the foam should be evaluated in its final form for compliance to existing standards in your industry. Nothing contained herein grants or extends a license, express or implied, in connection with patents, issued or pending, of the manufacturer or others. The information contained herein is based on the manufacturer's own study and the works of others. The manufacturer makes no warranties, expressed or implied, as to the accuracy, completeness, or adequacy of the information contained herein. The manufacturer shall not be liable (regardless of fault) to the vendee's employees, or anyone for any direct, special or consequential damages arising out of or in connection with the accuracy, completeness, adequacy or furnishing of such information.

ADDITIONAL SAFETY INFORMATION

Stepan Corporate Office

Polymer Department
22 West Frontage Road
Northfield, IL 60093

TEL (847) 446-7500

FAX (847) 441-1466

TECHSERV (800) 745-7837

techserv@stepan.com

Stepan Quimica Ltda. (Brazil)

Rua Pelotas 464
Vila Mariana

CEP 04012-001

Sao Paulo - SP

TEL +55-11-5089-2200

FAX +55-11-5539-4587

Stepan Europe (France)

BP127 Chemin Jongkind
38340 Voreppe

TEL +33-476-50-5100

FAX +33-476-50-5110

polyols-sales@stepan.com

europe.com

Stepan Jinling (China)

No. 92 Taixin Road
Nanjing, 210038

TEL +86-25-58976500

FAX +86-25-85597068

polyols-china@stepan.com

Stepan Company is a member of the American Chemistry Council and a charter member of Responsible Care.



Stepan® and STEPANPOL® are registered trademarks of Stepan Company.

Copyright© 2012, Stepan Company. All rights reserved.